



KINGSCOURT COUNTRY MANOR

— BRICKS —

TECHNICAL INFORMATION SHEET

FLB RICHMOND BLEND RED BRICK



Brand	Freshfield Lane
Colour	Red
Type	Stock-Pressed
Dimensions	215mm x 102.5mm x 65mm
Durability	F2
Active Soluble Salts	S2
Dimensional Tolerance & Range	T2, R1
Water Absorption	10%
Compressive Strength	29N/mm ²
Pack Size	400



DUBLIN

OUTH AUS GROUP, UNIT 26,
AIRWAYS INDUSTRIAL ESTATE, SANTRY,
DUBLIN 17, D17 TH93.
TEL: (01) 844 1205 - WEB: WWW.KCMB.IE

BELFAST

11B SHEEPWALK ROAD, LISBURN, COUNTY
ANTRIM,
BT28 3RD.
TEL: (028) 9077 7321 - WEB: WWW.KCMB.CO.UK

DISCLAIMER:

The reproduction of colours and textures is only as accurate as the printing process will allow. Photographic samples should be used when shortlisting products but we advise that an actual sample should be seen before ordering.

Important note: Sizes/dimensions can vary between firings. Please confirm your brick dimensions with your account manager prior to design or setting out.