


KINGSCOURT COUNTRY MANOR

- R	RΙ	CK	ς	

TECHNICAL INFORMATION SHEET

MORETON RED MULTI BRICK



Brand	Engels	
Colour	Red	
Туре	Solid Brick	
Dimensions	214mm x 101mm x 66mm	
Durability	F2	
Active Soluble Salts	S2	
Dimensional Tolerance & Range	T2, R1	
Water Absorption	14%	
Compressive Strength	10N/mm²	
Pack Size	600	
Active Soluble Salts Dimensional Tolerance & Range Water Absorption Compressive Strength	S2 T2, R1 14% 10N/mm²	



DUBLIN

OUTHAUS GROUP, UNIT 26, AIRWAYS INDUSTRIAL ESTATE, SANTRY, DUBLIN 17, D17 TH93.

TEL: (01) 844 1205 - WEB: WWW.KCMB.IE

BELFAST

11B SHEEPWALK ROAD, LISBURN, COUNTY ANTRIM, BT28 3RD.

TEL: (028) 9077 7321 - WEB: WWW.KCMB.CO.UK

DISCLAIMER:

The reproduction of colours and textures is only as accurate as the printing process will allow. Photographic samples should be used when shortlisting products but we advise that an actual sample should be seen before ordering.

Important note: Sizes/dimensions can vary between firings. Please confirm your brick dimensions with your account manager prior to design or setting out.